


## PRODUCT IMAGE

## TECHNICAL DRAWING





		$\overline{}$		1 1	$\sim$		_ ^	
$\boldsymbol{\nu}$	$\sim$	( )	1)	11	(	 ۱⊢	ΙДΙ	LS
	I 🔪	$\smile$	$\mathbf{\nu}$	$\cup$	$\cup$			

Basin Tap 1/2 Inch				
COS-CHR-103001M				
N.A				
M22X1 mm				
14.07 LPM @ 3 bar				
By using flow regulators (Product should be ordered with suffix as GA-6.0 LPM, GB-8.0 LPM, & GD-3.8 LPM @ 3.0 Bar pressure) one can regulate the flow rate				
0.5 Bar - 5 Bar				
Brass Ingots as per IS:1264-1997- Cu (58.0-63.0), Sn (0.0-1.0), Pb (0.5-2.5), Ni (0.0-1.0), Al (0.2-0.8), Mn (0.0-0.5), Total Impurity (0.0-2.0), Zn (Remainder)  Brass Rod as per IS:319-1989- Cu (56.0-59.0), Pb (2.0-3.5), Fe (0.0-0.35), Total Impurity (0.0-0.7), Zn (Remainder)  Brass Sheets as per IS:410-1977- Cu (61.5-64.5), Pb (0.0-0.3), Fe (0.0-0.075), Total Impurity (0.0-0.6), Zn (Remainder)				
<b>Fittings</b> : Components have WRAS Approved for food grade conformity with Brass Housing and Spindle Life Cycle EN 200: 200,000 cycles (Standard), - 4.0 LAC Cycles as per EN 200*				
12 bar (Pass)				
20 bar (pass)				
<b>Plating:</b> Nickel-8.0 micron Chromium-0.20 micron, Salt Spray (300 hrs + Validated), Adhesion (Pass)				
Chrome (CHR)				

DISCLAIMER: Our every effort has been made to ensure factual accuracy, the information presented subject to changes due to requirements in different sites, markets and/ or countries.110% variation in flow rate may be possible. Jaquar reserves the right to make the necessary amendments at any time without prior notice.